



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 256 460 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
13.11.2002 Bulletin 2002/46

(51) Int Cl.7: **B41M 5/00**

(21) Application number: 02076640.8

(22) Date of filing: 25.04.2002

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 07.05.2001 US 850026
07.05.2001 US 850027

(71) Applicant: **EASTMAN KODAK COMPANY**
Rochester, New York 14650 (US)

(72) Inventors:
• **Sadasivan, Sridhar**
Rochester, New York 14650-2201 (US)

• **Lobo, Lloyd Anthony**
Rochester, New York 14650-2201 (US)
• **Baier, John Marion**
Rochester, New York 14650-2201 (US)

(74) Representative:
Nunney, Ronald Frederick Adolphe et al
Kodak Limited,
Patents, W92-3A,
Headstone Drive
Harrow, Middlesex HA1 4TY (GB)

(54) **Ink jet recording element and printing method**

(57) An ink jet recording element comprising a support having thereon a porous image-receiving layer comprising at least 90% by weight of particles and less than 10% by weight of a binder, the image-receiving layer also containing a nonionic surfactant having an HLB

number of less than 10 in an amount to substantially prevent foaming of the coating composition which is used to coat the support with the image-receiving layer.

EP 1 256 460 A2

Description

[0001] This invention relates to an ink jet recording element, more particularly to a porous ink jet recording element and a printing method using the element.

[0002] In a typical ink jet recording or printing system, ink droplets are ejected from a nozzle at high speed towards a recording element or medium to produce an image on the medium. The ink droplets, or recording liquid, generally comprise a recording agent, such as a dye or pigment, and a large amount of solvent. The solvent, or carrier liquid, typically is made up of water and an organic material such as a monohydric alcohol, a polyhydric alcohol or mixtures thereof.

[0003] An ink jet recording element typically comprises a support having on at least one surface thereof an ink-receiving or image-receiving layer, and includes those intended for reflection viewing, which have an opaque support, and those intended for viewing by transmitted light, which have a transparent support.

[0004] An important characteristic of ink jet recording elements is their need to dry quickly after printing. To this end, porous recording elements have been developed which provide nearly instantaneous drying as long as they have sufficient thickness and pore volume to effectively contain the liquid ink. For example, a porous recording element can be manufactured by cast coating, in which a particulate-containing coating is applied to a support and is dried in contact with a polished smooth surface.

[0005] U.S. Patent 5,932,355 relates to an ink-jet recording sheet wherein the ink-receptive composition contains a non-ionic silicone surfactant, from about 14 to 93 % by weight of a polymer and a small amount of particulates such that the coating is transparent. However, there is a problem with this element in that it is not porous, so that it has a poor dry time.

[0006] U.S. Patent 5,919,559 relates to an inkjet recording sheet comprising an ink absorbing layer containing a predominant amount of water soluble resin or water dispersible resin and a nonionic surfactant having an HLB number of 11 or more. However, there is a problem with this element in that it is not porous, so that it will have a poor dry time.

[0007] It is an object of this invention to provide an ink jet recording element that is porous. It is another object of the invention to provide a printing method using the above described element.

[0008] These and other objects are achieved in accordance with the invention which comprise an ink jet recording element comprising a support having thereon a porous image-receiving layer comprising at least 90% by weight of particles and less than 10% by weight of a binder, the image-receiving layer also containing a nonionic surfactant having an HLB number of less than 10 in an amount to substantially prevent foaming of the coating composition which is used to coat the support with the image-receiving layer.

[0009] By use of the invention, a porous ink jet recording element is obtained which has a fast dry time and good image quality.

[0010] Another embodiment of the invention relates to an ink jet printing method comprising the steps of:

- A) providing an ink jet printer that is responsive to digital data signals;
- B) loading the printer with an ink jet recording element described above;
- C) loading the printer with an ink jet ink; and
- D) printing on the porous image-receiving layer using the ink jet ink in response to the digital data signals.

[0011] The presence of a binder in an image-receiving layer coating solution increases its propensity to foam. The coating solution typically requires a large amount of agitation to minimize the concentration gradients of the ingredients and thereby reduce variability. This agitation, however, typically leads to entrainment of air, which leads to the formation of excessive foam.

[0012] In accordance with the invention, certain non-ionic surfactants have been found to be antifoaming agents. In addition, these materials do not themselves foam at low concentrations.

[0013] As noted above, the non-ionic surfactants which are used in this invention have an HLB number less than 10. The HLB number of a surfactant is used to specify the nature of an oil/water dispersion that is formed in the presence of that surfactant. If the HLB number is less than 7, the dispersed (or drop) phase will be water. If the HLB number is above 12, the dispersed phase will be oil.

[0014] It has been found that the HLB number can also be used to predict the ability of a nonionic surfactant to eliminate foam in a coating solution. If a surfactant has an HLB number of 10 or greater, the surfactant may enhance the stability of the foam instead of eliminating it.

[0015] The HLB number of surfactants can be measured or calculated. There are several methods of measuring HLB, some of which are listed in "Nonionic Surfactants", Ed. M. Schick, "Surfactant Science Series", Vol. 1, Marcel Dekker Inc., New York, 1967.

[0016] There are several kinds of nonionic surfactants that can be used in the present invention. There can be used,

for example, ethoxylated alcohols having the formula $R-O(CH_2CH_2O)_nH$ where R can be alkyl, aryl or aralkyl having from 2 to 30 carbon atoms and n can vary from 2 to 20. The HLB number of an ethoxylated alcohol is related to the ratio of the number of ethylene oxide groups to the number of carbon atoms in the R group. Preferred ethoxylated alcohols useful in the invention include those where all or some of the hydrogen atoms in the R group are substituted by fluorine atoms.

[0017] Another class of nonionic surfactants useful in the invention is the block copolymers of ethylene oxide and propylene oxide. Examples of these are Pluronics® (poloxamers) which are triblock copolymers and Tetronics® (poloxamines), which are tetrafunctional block copolymers derived from the sequential addition of propylene oxide and ethylene oxide to ethylenediamine. The ratio of the amount of propylene oxide to ethylene oxide is directly related to the HLB number of the surfactant.

[0018] Another class of nonionic surfactants useful in the invention is alkoxyated poly(dimethylsiloxanes) (PDMS) or polyalkylene-modified PDMS materials, including those containing ethylene oxide as well as ethylene oxide and propylene oxide and having an HLB number as described above.

[0019] Another class of nonionic surfactants useful in the invention is based on derivatives of mono and disaccharides, including sorbitol esters such as Spans®, and alkyl glucosides and hydrophobic sucrose esters such as sucrose distearate.

[0020] Commercial examples of the above surfactants useful in the invention include:

S-1	Silwet® L7220 (Witco Corp.)
S-2	Silwet® L7210 (Witco Corp.)
S-3	Silwet® L7602 (Witco Corp.)
S-4	Pluronic® L61 (BASF Corp.)
S-5	Tetronic® 90R4 (BASF Corp.)
S-6	Tetronic® 701 (BASF Corp.)
S-7	Tetronic® 150R1 (BASF Corp.)
S-8	Fluorad® FC171 (3M Corp.)
S-9	Brij® 30 (ICI Chemicals)
S-10	Brij® 93 (ICI Chemicals)

[0021] The surfactants used in the present invention are typically used in relatively small amounts. Based on their HLB numbers, these surfactants have limited solubility in coating solutions. These surfactants have a cloud point, which is the highest temperature at which the surfactant is soluble in water.

Coating operations typically take place between 25 and 30°C. Therefore, these surfactants are usually used at levels below their solubility limit at the operating temperature. In general, the surfactants may be used in an amount of at least 0.05 % by weight of the coating solution, preferably from 0.05 % to 1.0 % by weight.

[0022] Examples of particles useful in the invention include alumina, boehmite, clay, calcium carbonate, titanium dioxide, calcined clay, aluminosilicates, silica, barium sulfate, or polymeric beads. The particles may be porous or nonporous. In a preferred embodiment of the invention, the particles are inorganic such as alumina, silica, fumed alumina or fumed silica. Such particles are preferred for ink jet recording elements because they possess positively charged surfaces, which are capable of binding anionic ink jet printing dyes, rendering printed images resistant to dye migration due to water and high humidity conditions.

[0023] As noted above, the porous image-receiving layer comprises at least 90% by weight of particles. This amount of particles will insure that the layer is porous, i.e., have interconnecting voids so that the solvent in the ink can travel through the layer to a support or base layer if one is present. In a preferred embodiment, the porous image-receiving layer comprises at least 90-95% by weight of particles.

[0024] In general, any binder may be used in the invention. In a preferred embodiment, the binder is a hydrophilic polymer such as poly(vinyl alcohol), poly(vinyl pyrrolidone), gelatin, cellulose ethers, poly(oxazolines), poly(vinylacetamides), partially hydrolyzed poly(vinyl acetate/vinyl alcohol), poly(acrylic acid), poly(acrylamide), poly(alkylene oxide), sulfonated or phosphated polyesters and polystyrenes, casein, zein, albumin, chitin, chitosan, dextran, pectin, collagen derivatives, collodion, agar-agar, arrowroot, guar, carrageenan, tragacanth, xanthan, rhamnan and the like. In still another preferred embodiment of the invention, the hydrophilic polymer is poly(vinyl alcohol), hydroxypropyl cellulose, hydroxypropyl methyl cellulose, gelatin, or a poly(alkylene oxide). In yet still another preferred embodiment, the hydrophilic binder is poly(vinyl alcohol). The polymeric binder should be chosen so that it is compatible with the aforementioned particles.

[0025] The amount of binder used in the invention should be sufficient to impart cohesive strength to the ink jet recording element, but should also be minimized so that the interconnected pore structure formed by the particles is not filled in by the binder. In a preferred embodiment of the invention, the amount of binder employed is less than 10% by weight, preferably 5-10 % by weight.

[0026] The thickness of the image-receiving layer may range from 5 to 40 μm , preferably from 10 to 20 μm . The coating thickness required is determined through the need for the coating to act as a sump for absorption of ink solvent and the need to hold the ink near the coating surface. The coating may be applied in a single layer or in multiple layers so the functionality of each coating layer may be specified. For example, a two-layer structure can be created wherein the base layer functions as a sump for absorption of ink solvent while the top layer holds the ink. In that case, the nonionic surfactant and particles are used in both layers, i.e., the base layer contains at least 90% by weight of particles and less than 10% by weight of a binder, and the base layer also contains a nonionic surfactant having an HLB number of less than 10 in an amount to substantially prevent foaming of the coating composition which is used to coat the support with the base layer.

[0027] After coating, the ink jet recording element may be subject to calendaring or supercalendering to enhance surface smoothness. In a preferred embodiment of the invention, the ink jet recording element is subject to hot, softnip calendaring at a temperature of 65°C and pressure of 14000 kg/m at a speed of from 0.15 m/s to 0.3 m/s.

[0028] The support for the ink jet recording element used in the invention can be any of those usually used for ink jet receivers, such as resincoated paper, paper, polyesters, or microporous materials such as polyethylene polymer-containing material sold by PPG Industries, Inc., Pittsburgh, Pennsylvania under the trade name of Teslin®, Tyvek® synthetic paper (DuPont Corp.), and OPPalite® films (Mobil Chemical Co.) and other composite films listed in U.S. Patent 5,244,861. Opaque supports include plain paper, coated paper, synthetic paper, photographic paper support, melt-extrusion-coated paper, and laminated paper, such as biaxially oriented support laminates. Biaxially oriented support laminates are described in U.S. Patents 5,853,965; 5,866,282; 5,874,205; 5,888,643; 5,888,681; 5,888,683; and 5,888,714. These biaxially oriented supports include a paper base and a biaxially oriented polyolefin sheet, typically polypropylene, laminated to one or both sides of the paper base. Transparent supports include glass, cellulose derivatives, e.g., a cellulose ester, cellulose triacetate, cellulose diacetate, cellulose acetate propionate, cellulose acetate butyrate; polyesters, such as poly(ethylene terephthalate), poly(ethylene naphthalate), poly(1,4-cyclohexanedimethylene terephthalate), poly(butylene terephthalate), and copolymers thereof; polyimides; polyamides; polycarbonates; polystyrene; polyolefins, such as polyethylene or polypropylene; polysulfones; polyacrylates; polyetherimides; and mixtures thereof. The papers listed above include a broad range of papers, from high end papers, such as photographic paper to low end papers, such as newsprint.

[0029] The support used in the invention may have a thickness of from 50 to 500 μm , preferably from 75 to 300 μm . Antioxidants, antistatic agents, plasticizers and other known additives may be incorporated into the support, if desired.

[0030] Coating compositions employed in the invention may be applied by any number of well known techniques, including dip-coating, wound-wire rod coating, doctor blade coating, gravure and reverse-roll coating, slide coating, bead coating, extrusion coating, curtain coating and the like. Known coating and drying methods are described in further detail in Research Disclosure no. 308119, published Dec. 1989, pages 1007 to 1008. Slide coating is preferred, in which the base layers and overcoat may be simultaneously applied. After coating, the layers are generally dried by simple evaporation, which may be accelerated by known techniques such as convection heating.

[0031] In order to impart mechanical durability to an ink jet recording element, crosslinkers which act upon the binder discussed above may be added in small quantities. Such an additive improves the cohesive strength of the layer. Crosslinkers such as carbodiimides, polyfunctional aziridines, aldehydes, isocyanates, epoxides, polyvalent metal cations, and the like may all be used.

[0032] To improve colorant fade, UV absorbers, radical quenchers or antioxidants may also be added to the image-receiving layer as is well known in the art. Other additives include adhesion promoters, rheology modifiers, biocides, lubricants, dyes, optical brighteners, matte agents, antistatic agents, etc.

[0033] The coating composition can be coated so that the total solids content will yield a useful coating thickness, and for particulate coating formulations, solids contents from 10-60% are typical.

[0034] Ink jet inks which can be used to image the recording elements of the present invention are well-known in the art. The ink compositions used in ink jet printing typically are liquid compositions comprising a solvent or carrier liquid, dyes or pigments, humectants, organic solvents, detergents, thickeners, preservatives, and the like. The solvent or carrier liquid can be solely water or can be water mixed with other water-miscible solvents such as polyhydric alcohols. Inks in which organic materials such as polyhydric alcohols are the predominant carrier or solvent liquid may also be used. Particularly useful are mixed solvents of water and polyhydric alcohols. The dyes used in such compositions are typically water-soluble direct or acid type dyes. Such liquid compositions have been described extensively in the prior art including, for example, U.S. Patents 4,381,946; 4,239,543 and 4,781,758.

[0035] The following examples further illustrate the invention.

Example 1-Surfactant in Image-receiving Layer Coating Solution

[0036] Coating solution 1 was prepared by mixing 100 dry g of Dispak® 14N4-80 alumina (Condea Vista Co.) as a 20% solution with 4 dry g of poly(vinyl alcohol) GH-17® (Nippon Gohsei Co. Ltd.) as a 10% solution and 0.1 dry g of

2,3-dihydroxy-1,4-dioxane (Clariant Corp). The solids of the coating solution was adjusted to 20% by adding water.
[0037] The nonionic surfactants S-1 through S-10 described above were compared to the performance of control surfactants C-1 through C-4, identified below, whose HLB numbers are outside the range of this invention. All surfactants were added to the coating solution at a level of 0.5 % by weight.

- 5
 C-1 Silwet ® L7500 (Witco Corp.)
 C-2 Pluronic® F108 (BASF Corp.)
 C-3 Tetronic® 904 (BASF Corp.)
 C-4 Triton ® X-45 (Union Carbide Corp.)

10 **[0038]** The HLB numbers of all surfactants employed are based on the values reported by the respective manufacturer, except where noted.

[0039] About 20 ml of the coating solution was placed in a 50 ml graduated cylinder which had a diameter of 1 cm. It was then manually shaken until the foam height remained constant. After the shaking was stopped, the initial foam volume (total volume of the coating solution and associated foam) was noted. The volume of the foam was noted again after 30 minutes.

15 **[0040]** If the foam height had reduced to about 20 ml, the surfactant is deemed effective. If the foam height remained high even after 30 minutes, the surfactant is considered to be ineffective. The results are shown in Table 1 below.

Table 1

Surfactant	HLB	Initial foam volume	Volume after 30 minutes	Effectiveness
None	N/A	41	40	N/A
S-1	5-8	23	21	Yes
S-2	5-8	23	21	Yes
S-3	5-8	24	20	Yes
S-4	3	20	20	Yes
S-5	7	25	21	Yes
S-6	3	25	20	Yes
S-7	1	26	21	Yes
S-8	2.8*	22	21	Yes
S-9	9.7	27	21	Yes
S-10	4.9	21	21	Yes
C-1	13	37	37	No
C-2	27	46	46	No
C-3	15	40	38	No
C-4	10.4	44	40	No

*calculated

45 **[0041]** The above results show that the non-ionic surfactants of the invention were effective in reducing foam as compared to the surfactants whose HLB number is above the number described in the invention

Example 2-Surfactant in Base Layer Coating Solution

50 **[0042]** Coating solution 2 was prepared by mixing 100 dry g of Albagloss-s® precipitated calcium carbonate (Speciality Minerals Inc.) as a 70% solution with 5 dry g of poly(vinyl alcohol) GH-17® (Nippon Gohsei Co., Ltd.) as a 10% solution and 0.1 dry g of 2,3-dihydroxy-1,4-dioxane (Clariant Corp). The solids of the coating solution was adjusted to 35% by adding water.

55 **[0043]** The same surfactants were added to the base coating composition and tested as in Example I and the results are shown in Table 2 below:

Table 2

Surfactant	HLB	Initial foam volume	Volume after 30 minutes	Effectiveness
None	N/A	36	36	N/A
S-1	5-8	26	21	Yes
S-2	5-8	25	23	Yes
S-3	5-8	28	26	Yes
S-4	3	29	26	Yes
S-5	7	25	21	Yes
S-6	3	32	25	Yes
S-7	1	27	22	Yes
S-8	2.8*	30	26	Yes
S-9	9.7	27	21	Yes
S-10	4.9	21	21	Yes
C-1	13	39	37	No
C-2	27	43	46	No
C-3	15	42	38	No
C-4	10.4	43	40	No

*calculated

[0044] The above results show that the non-ionic surfactants of the invention were effective in reducing foam as compared to the surfactants whose HLB number is above the number described in the invention

Example 3- Printing on Recording Element

[0045] The base layer coating solution from Example 2 was bead-coated at 25 ° C on a base paper and dried at 60°C by forced air. The base paper used was Nekoosa Solutions Smooth ® (Georgia Pacific), Grade 5128 (Carrara White ®, Color 9220), basis weight 150 g/m². The image-receiving layer coating solution of Example 1 was coated on top of this base layer. The recording element was then dried at 60 ° C by forced air to yield a two-layer recording element in which the thicknesses of the bottom and topmost layers were 25 µm (27 g/m²) and 8 µm (8.6 g/m²), respectively.

[0046] Test images of cyan, magenta, yellow, red, green and blue patches at 100% ink laydown were printed on the above recording element using an Epson Stylus® Color 740 using inks with catalogue number S020191. Immediately after ejection from the printer, a piece of bond paper was placed over the printed image and rolled with a smooth, heavy weight. Then the bond paper was separated from the printed image. Ink transferred to the bond paper if the recording element was not dry. The length of the transferred image on the bond paper was measured and is proportional to the dry time. Dry times corresponding to a length of about 40 cm or less are acceptable.

[0047] After drying for 24 hours at ambient temperature and humidity, the Status A D-max densities were measured using an X-Rite® 820 densitometer as follows (for each of the red, green and blue densities, the two component-color densities were measured and averaged). The results are shown in table 3.

Table 3

Dry Time (cm)	Status A D-max Density					
	Cyan	Magenta	Yellow	Red	Green	Blue
0	2.28	1.99	1.79	1.96	2.13	2.31

[0048] The above results show that the ink jet recording element of the invention has good image optical density and an apparent instant dry time (No ink was transferred to the bond paper immediately after printing).

Claims

1. An ink jet recording element comprising a support having thereon a porous image-receiving layer comprising at least 90% by weight of particles and less than 10% by weight of a binder, said image-receiving layer also containing a nonionic surfactant having an HLB number of less than 10 in an amount to substantially prevent foaming of the coating composition which is used to coat said support with said image-receiving layer.
2. The recording element of Claim 1 wherein said nonionic surfactant is present in an amount of at least 0.05 % by weight.
3. The recording element of Claim 1 wherein said nonionic surfactant is present in an amount of from 0.05 % to 1.0% by weight.
4. The recording element of Claim 1 wherein said surfactant is an ethoxylated alcohol, a polypropylene oxide-polyethylene oxide block copolymer or an alkoxyated poly(dimethyl siloxane).
5. The recording element of Claim 1 wherein said particles are inorganic.
6. The recording element of Claim 5 wherein said inorganic particles comprise alumina, silica, fumed alumina or fumed silica.
7. The recording element of Claim 1 wherein said binder is a hydrophilic binder.
8. The recording element of Claim 7 wherein said hydrophilic binder is poly(vinyl alcohol).
9. The recording element of Claim 1 wherein a base layer is present between said support and said image-receiving layer.
10. An ink jet printing method, comprising the steps of:
 - A) providing an ink jet printer that is responsive to digital data signals;
 - B) loading said printer with an ink jet recording element as described in Claim 1;
 - C) loading said printer with an ink jet ink; and
 - D) printing on said porous image-receiving layer using said ink jet ink in response to said digital data signals.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 256 460 A3

EUROPEAN PATENT APPLICATION

(12)

(88) Date of publication A3:
05.01.2005 Bulletin 2005/01

(51) Int Cl.7: **B41M 5/00**

(43) Date of publication A2:
13.11.2002 Bulletin 2002/46

(21) Application number: **02076640.8**

(22) Date of filing: **25.04.2002**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **07.05.2001 US 850026**
07.05.2001 US 850027

(71) Applicant: **EASTMAN KODAK COMPANY**
Rochester, New York 14650 (US)

(72) Inventors:
• **Sadasivan, Sridhar**
Rochester, New York 14650-2201 (US)
• **Lobo, Lloyd Anthony**
Rochester, New York 14650-2201 (US)
• **Baler, John Marlon**
Rochester, New York 14650-2201 (US)

(74) Representative: **Haile, Helen Cynthia et al**
Kodak Limited
Patent Department, W92-3A,
Headstone Drive
Harrow, Middlesex HA1 4TY (GB)

(54) **Ink jet recording element and printing method**

(57) An ink jet recording element comprising a support having thereon a porous image-receiving layer comprising at least 90% by weight of particles and less than 10% by weight of a binder, the image-receiving layer also containing a nonionic surfactant having an HLB

number of less than 10 in an amount to substantially prevent foaming of the coating composition which is used to coat the support with the image-receiving layer.

EP 1 256 460 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 07 6640

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	PATENT ABSTRACTS OF JAPAN vol. 0100, no. 06 (M-445), 11 January 1986 (1986-01-11) & JP 60 171190 A (MISHIMA SEISHI KK), 4 September 1985 (1985-09-04) * abstract *	1-10	B41M5/00
A	PATENT ABSTRACTS OF JAPAN vol. 0113, no. 72 (M-648), 4 December 1987 (1987-12-04) & JP 62 144986 A (CANON INC), 29 June 1987 (1987-06-29) * abstract *	1-10	
A	EP 1 078 774 A (HEWLETT PACKARD CO) 28 February 2001 (2001-02-28) * abstract * * example 1 *	1-10	
A	EP 1 080 936 A (FERRANIA S P A) 7 March 2001 (2001-03-07) * abstract * * paragraphs [0019] - [0024], [0031] - [0034], [0038] - [0040] *	1-10	TECHNICAL FIELDS SEARCHED (Int.Cl.7) B41M
A	US 5 364 702 A (IDEI KOUJI ET AL) 15 November 1994 (1994-11-15) * column 1, line 64 - column 2, line 37 *	1-10	
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 11 November 2004	Examiner Vogel, T
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document		T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document	

EPO FORM 1503 (03/02) (PC/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 07 6640

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

11-11-2004

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
JP 60171190	A	04-09-1985	JP	1629172 C	20-12-1991
			JP	2057026 B	03-12-1990

JP 62144986	A	29-06-1987	US	4868581 A	19-09-1989

EP 1078774	A	28-02-2001	EP	1078774 A2	28-02-2001
			JP	2001113823 A	24-04-2001
			US	2003203134 A1	30-10-2003

EP 1080936	A	07-03-2001	IT	SV990026 A1	05-03-2001
			DE	60010189 D1	03-06-2004
			EP	1080936 A2	07-03-2001
			US	6387473 B1	14-05-2002

US 5364702	A	15-11-1994	JP	3043291 A	25-02-1991
			JP	3126128 B2	22-01-2001
			DE	4022008 A1	17-01-1991

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☒ **FADED TEXT OR DRAWING**

☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.